



Tile Redi® Installation Guide Redi POXY® - Setting Material Epoxy Adhesive

Mixing:

Pour Redi POXY® Epoxy Adhesive Part A and Part B into a clean mixing pail and mix thoroughly. Add Redi POXY® Part C Filler Powder and mix to a smooth, trowelable consistency. Mortar is ready for use immediately after mixing.

Packaging:

Redi POXY® Epoxy Adhesive is a factory proportioned kit with resin, hardener, and filler powder.

Unit Size: Unit Sizes

#1 Unit - Weight 6 lb. (2.72 kg)

#2 Unit - Weight 9 lb. (4.08 kg)

#3 Unit - Weight 12.6 lb. (5.71 kg)

Approximate Coverage

	Unit #1 6 lb.	Unit #2 9 lb.	Unit #3 12.6 lb.
With 1/6" (1.5mm) v-notch trowel	45-50 sq. ft./4.2-4.6 m ²	65-75 sq. ft./6.0-6.9 m ²	90-100 sq. ft./8.1-9.0 m ²
With 3/16" (4mm) v-notch trowel	17-20 sq. ft./1.6-1.9 m ²	26-30 sq. ft./2.4-2.8 m ²	35-40 sq. ft./3.2-3.6 m ²
With 1/8" x 1/8" (3x3 mm) square notch trowel	22-27 sq. ft./2.0-2.5 m ²	33-41 sq. ft./3.1-3.8 m ²	45-55 sq. ft./4.2-5.1 m ²
With 1/4" x 1/4" (6x6 mm) square notch trowel	7-9 sq. ft./0.7-0.8 m ²	11-13 sq. ft./1.0-1.2 m ²	15-18 sq. ft./1.4-1.7 m ²

Working Properties (70°F [21°C])

- Pot Life 45 minutes
- Time to Grout 12 hours
- Time to Light Traffic 12 hours
- Time to Heavy Traffic 24 hours
- Minimum Application Layer 1/8 in (3mm)
- Maximum Application Layer 3/8 in (9mm)
- Wet Density 99 lbs/ft³ (1590 kg/m³)